



Company Address	W. L. Gore & Associates GmbH, Hermann-Oberth-Strasse 22, 85640 Putzbrunn, Germany	According to <b>DIN EN 13555</b> 2014-07
Gasket Type	GORE® GR Sheet Gasketing	
Sealing element dimensions [mm]	92 x 49 x 1.5	

L [mg/(s·m)]	Q <sub>min/L</sub> [MPa]	Q <sub>Smin/L</sub> [MPa]										
		Q <sub>A</sub> = 20 MPa	Q <sub>A</sub> = 30 MPa	Q <sub>A</sub> = 40 MPa	Q <sub>A</sub> = 60 MPa	Q <sub>A</sub> = 80 MPa						
10 <sup>0</sup>	10	10	10	10	10	10						
10 <sup>-1</sup>	10	10	10	10	10	10						
10 <sup>-2</sup>	20	10	10	10	10	10						
10 <sup>-3</sup>	33			10	10	10						
10 <sup>-4</sup>	42				10	10						
10 <sup>-5</sup>	54					10						




L [mg/(s·m)]	Q <sub>min/L</sub> [MPa]	Q <sub>Smin/L</sub> [MPa]										
		Q <sub>A</sub> = 20 MPa	Q <sub>A</sub> = 30 MPa	Q <sub>A</sub> = 40 MPa	Q <sub>A</sub> = 60 MPa	Q <sub>A</sub> = 80 MPa						
10 <sup>0</sup>	10	10	10	10	10	10						
10 <sup>-1</sup>	13	10	10	10	10	10						
10 <sup>-2</sup>	26		10	10	10	10						
10 <sup>-3</sup>	37			16	10	10						
10 <sup>-4</sup>	48				10	10						
10 <sup>-5</sup>	59				16	10						



Note: the content of darkened cells was not determined respectively is unnecessary      Rev - No: 2      Creation date of this sheet: 2016-01-25

Company Address	W. L. Gore & Associates GmbH, Hermann-Oberth-Strasse 22, 85640 Putzbrunn, Germany	According to <b>DIN EN 13555</b> 2014-07
Gasket Type	GORE® GR Sheet Gasketing	
Sealing element dimensions [mm]	92 x 49 x 1.5	

L [mg/(s*m)]	Q <sub>min,L</sub> [MPa]	Minimum stress to seal Q <sub>min,L</sub> (at assembly), Q <sub>Smin,L</sub> (after off-loading) for p = 40 bar												
		Q <sub>Smin,L</sub> [MPa]												
		Q <sub>A</sub> = 20 MPa	Q <sub>A</sub> = 30 MPa	Q <sub>A</sub> = 40 MPa	Q <sub>A</sub> = 60 MPa	Q <sub>A</sub> = 80 MPa								
10 <sup>0</sup>	10	10	10	10	10	10								
10 <sup>-1</sup>	19	19	10	10	10	10								
10 <sup>-2</sup>	32			10	10	10								
10 <sup>-3</sup>	43			10	10	10								
10 <sup>-4</sup>	53				10	10								
10 <sup>-5</sup>	77					52								



Note: the content of darkened cells was not determined respectively is unnecessary      Rev - No: 2      Creation date of this sheet: 2016-01-25

